



BaseGrid 22

3904 Virginia Ave • Cincinnati, Ohio 45227 • Phone (513) 271-6000 • Fax (513) 271-4420

MULTILAYER BI-ORIENTED GEOGRIDS

US Fabrics Inc BaseGrid 22 is composed of two layers of high strength extruded biaxially oriented polypropylene geogrids. The layers are welded and rolled together without superimposing the grids creating a geogrid with random sized apertures designed to accommodate a variety of fill materials. The random aperture geometry, many tensile elements, and multiple layers of the geogrid enhance soil/geogrid interaction.

US Fabrics Inc BaseGrid 22 geogrid greatly improves the geogrid interlocking capacity, distributes applied loads, and prevents localized shear failure.

TYPICAL APPLICATIONS

Soft soil stabilization • Base reinforcement • Embankments over soft soils • Working platforms • Haul roads

MATERIAL CHARACTERISTICS	TEST METHOD	DATA
Polymer Type		Polypropylene
Carbon Black Content	ASTM D 4218	0.50%

TECHNICAL CHARACTERISTICS	TEST METHOD	UNIT	BaseGrid 22		NOTES
			MD	TD	
Strengths and Load Capacity:					
Peak Tensile Strength	ASTM D 6637	lb/ft (kN/m)	925 (13.5)	1,400 (20.5)	a,c,d
True Tensile Strength in Use: @ 2% Strain	ASTM D 6637	lb/ft (kN/m)	301 (4.4)	450 (6.57)	a,c,d
@ 5% Strain			616 (9.0)	920 (13.42)	a,c,d
True Initial Modulus in Use	ASTM D 6637	lb/ft (kN/m)	17,140 (250)	27,420 (400)	a,c,d
Tensile Modulus: @ 2% Strain	ASTM D 6637	lb/ft (kN/m)	15,050 (220)	22,500 (328)	a,c,d
@ 5% Strain			12,320 (180)	18,400 (269)	a,c,d
Structural Integrity:					
Junction Tensile Strength: @ 1% Strain	GRI-GG2	lb/ft (kN/m)	170 (2.48)	200 (2.92)	b,d
@ 2% Strain			235 (3.44)	300 (4.38)	b,d
Junction Tensile Modulus: @ 1% Strain	GRI-GG2	lb/ft (kN/m)	17,000 (248)	20,000 (292)	b,d
@ 2% Strain			11,780 (172)	15,000 (219)	b,d
Junction: Strength Efficiency	GRI-GG2	lb/ft (kN/m) %	860 (12.55) 90	1,315 (19.2) 90	a,d a,d
Flexural Rigidity	ASTM D 1388	mg-cm	250,000	250,000	b
Pullout Coefficient of Interaction	ASTM D 6707		> 1.0	> 1.0	e
Durability:					
Resistance to Installation Damage	ASTM D 5818	%SC/%SW/%GP	>90/>90/90	>90/>90/90	f

DIMENSIONAL CHARACTERISTICS	TEST METHOD	UNIT	BaseGrid 22	NOTES
Open Area		%	75	a
Unit Weight	ASTM D 5261	oz/yd ² (g/m ²)	6.5 (220)	b
Roll Dimensions		ft x ft (m x m)	13.1 x 328 (4 x 100)	b
Roll Area		yd ² (m ²)	478 (400)	b
Gross Roll Weight		lb (kg)	231 (105)	b

NOTES

a) 95% lower confidence limit values, ISO 2602	d) Single layer value	f) Tenax report GRID-TE-4: "Construction Damage Tests of Geogrids"
b) Typical value	e) MD: Machine direction (longitudinal to the roll) TD: Transversal direction (across the roll width)	
c) Tests performed using extensometers		

The geosynthetic industry has not identified any values for the index property Torsional Stiffness (Secant Aperture Stability Modulus), nor has the test method been developed as an industry standard (ASTM or GRI). Therefore, accredited geosynthetic independent labs cannot evaluate a product per this method. The above information is to the best of our knowledge accurate, but is not intended to be considered as a guarantee. Any implied warranty for a particular use or purpose is excluded. If the Product does not meet the above properties, and notice is given to US Fabrics, Inc., the product will be replaced or refunded. (1/2009).