




# SG 150



3904 Virginia Ave • Cincinnati, Ohio 45227 • Phone (513) 271-6000 • Fax (513) 271-4420

## Bi-Axial Knitted Geogrid

**STRATAGRID** is geogrid reinforcement for soil. These high performance geogrids are constructed of high molecular weight and high tenacity polyester yarns utilizing a complex knitting process and low temperature coating technology to provide superior engineering properties. Yarns are precision knitted into a dimensionally stable, uniform network of apertures providing significant tensile reinforcement capacity. STRATAGRID is engineered to be mechanically and chemically durable, in both the harsh construction installation phase and in aggressive soil environments (pH range from 2-10). A proprietary UV stabilized coating provides further chemical and mechanical benefits.

PROPERTY	TEST METHOD	ENGLISH	METRIC
Ultimate Strength	ASTM D-6637 METHOD A	1875 lbs/ft	27.4 kN/m
Creep Limited Strength	ASTM D-5262	1210 lbs/ft	17.7 kN/m
Long Term Design Strength (LTDS)	FHWA NHI-00-043		
	Sand, Silt & Clay	916 lbs/ft	13.4 kN/m
	¾" minus angular aggregate	815 lbs/ft	11.9 kN/m
	1.5" minus angular aggregate	786 lbs/ft	11.5 kN/m

PROPERTY	ENGLISH	METRIC
Roll Dimensions (Width X Length)	6ft x 150ft 12ft x 150ft	1.83m x 45.7m 3.66m x 45.7m
Area	100 / 200 SY	83.6 / 167.2 SM
Roll Weight	45 / 90 lbs	20.4 / 40.9 kg

REDUCTION FACTORS FOR INSTALLATION DAMAGE & DURABILITY	
RF <sub>installation damage</sub> (Sand, Silt & Clay, D <sub>50</sub> < 0.6mm)	1.05
RF <sub>installation damage</sub> (¾" minus angular aggregate, D <sub>50</sub> < 6mm)	1.10
RF <sub>installation damage</sub> (1.5" minus angular aggregate, D <sub>50</sub> < 20mm)	1.20
RF <sub>durability</sub>	1.10
SOIL INTERACTION COEFFICIENTS FOR PULLOUT (C <sub>i</sub> ) & DIRECT SLIDING (C <sub>DS</sub> )	
Sand/Clay (ML, CL)	0.6 - 0.7
Sandy Silts & Clay (SC, GC)	0.7 - 0.8
Uniformly-Graded Sands, Silty Sand (SP, SM)	0.8 - 0.9
Gravel, Sand Gravel Mix, Well-Graded Sand (SW, GP, GW)	0.9 - 1.0

The above information is to the best of our knowledge accurate, but is not intended to be considered as a guarantee. Any implied warranty for a particular use or purpose is excluded. If the Product does not meet the above properties, and notice is given to US Fabrics, Inc., the product will be replaced or refunded. (1/2009).