




# DuPont SF 32

## Spunbond Nonwoven Geotextile



DuPont SF 32 is a nonwoven, spunbonded, continuous filament, polypropylene geotextile offering the consistent quality expected of spunbond geotextiles. DuPont SF 32 resists ultraviolet and biological deterioration, rotting, naturally encountered basics and acids. Polypropylene is stable within a pH range of 2 to 13. DuPont SF 32 meets the following M.A.R.V. values except where noted:



PROPERTY	TEST METHOD	ENGLISH	METRIC
Weight	<a href="#">ASTM D-5261</a>	3.2 oz/y <sup>2</sup>	108.48 g/m <sup>2</sup>
Grab Tensile Strength	<a href="#">ASTM D-4632</a>	110 lbs	490 N
Elongation @ Break	<a href="#">ASTM D-4632</a>	50 %	50 %
Mullen Burst <sup>(3)</sup>	<a href="#">ASTM D-3786</a>	90 psi	620 kPa
Pin Puncture <sup>(3)</sup>	<a href="#">ASTM D-4833</a>	30 lbs	134 N
CBR Puncture	<a href="#">ASTM D-6241</a>	209 lbs	930 N
Trapezoidal Tear	<a href="#">ASTM D-4533</a>	54 lbs	240 N
Apparent Opening Size <sup>(1,2)</sup>	<a href="#">ASTM D-4751</a>	50 US Sieve	0.297 mm
Permittivity <sup>(1)</sup>	<a href="#">ASTM D-4491</a>	1.3 Sec <sup>-1</sup>	1.3 Sec <sup>-1</sup>
Permeability <sup>(1)</sup>	<a href="#">ASTM D-4491</a>	0.05 cm/sec	0.05 cm/sec
Water Flow Rate <sup>(1)</sup>	<a href="#">ASTM D-4491</a>	95 g/min/f <sup>2</sup>	3,870 L/min/m <sup>2</sup>
UV Resistance @ 500 Hours	<a href="#">ASTM D-4355</a>	50 %	50 %

<sup>(1)</sup> At the time of manufacturing. Handling, storage, and shipping may change these properties.

<sup>(2)</sup> Maximum average roll value (MaxARV).

<sup>(3)</sup> Historical reference values. These properties are no longer recognized by ASTM or AASHTO for geosynthetics.

## DuPont SF 32 Shipping & Packaging Information

SIZE	DIAMETER	WIDTH	WEIGHT	AREA	ROLLS PER TRAILER
12' x 300'	7"	12'	100 lbs	400 y <sup>2</sup>	500

**US Fabrics, Inc. | 3904 Virginia Avenue | Cincinnati, OH 45227**  
**Phone: (800) 518-2290 | Fax: (513) 271-4420 | email: [info@usfabrics.com](mailto:info@usfabrics.com)**

This information is provided for reference only and is not intended as a warranty or guarantee.  
 US Fabrics assumes no liability in connection with the use of this information.