







- 40 mil thick composite member.
- Reinforced polyolefin base, laminated to a polypropylene layer.
- Adhesive-backed with removable release liner.

PROPERTY	TEST METHOD	ENGLISH	METRIC
Mullen Burst	ASTM 0751-95	180 x 1,240.92 psi	kPa
Trapezoidal Tear	ASTM 04533-91	46 x 44 lbs	205 x 196 N
Tensile Strength	ASTM 0751-95	130 x 124 lbs	579 x 552 N
Permeability (MVTR)	ASTM E96-8	0.075 Perms	0.075 Perms
Recycled Content	Calculated	45 %	45 %
UV Resistance @ 2,000 Hours	ASTM G154-98	90 %	90 %

AWD Fitting & Joint Tape Shipping & Packaging Information

SIZE

4" x 75'