




Baselok 2,200 lb Polyester Tendon



A 2,200 lb. (9.34 kN) polyester, woven tendon designed for use with Baselok geocell.



PROPERTY	TEST METHOD	ENGLISH	METRIC
Breaking Strength (Min - Max) <input type="radio"/> Warp		2,280 - 2,520 lbs	10.14 x 11.21 kN
Breaking Strength (Min - Max) <input type="radio"/> Fill		155 lbs	0.69 kN
Elongation @ Break (min - Max) <input type="radio"/> Warp		9 x 15 %	9 x 15 null
Elongation @ Break (min - Max) <input type="radio"/> Fill		9 x 15 %	9 x 15 null

US Fabrics, Inc. | 3904 Virginia Avenue | Cincinnati, OH 45227

Phone: (800) 518-2290 | Fax: (513) 217-4420 | email: info@usfabrics.com

This information is provided for reference only and is not intended as a warranty or guarantee.
US Fabrics assumes no liability in connection with the use of this information.