





SGU60

Uni-Axial Knitted Geogrid

RETAINING WALL



STRATAGRID SGU60 (formerly SG200) is engineered to be mechanically and chemically durable, in both the harsh construction installation phase and in aggressive soil environments (pH range from 3-9). STRATAGRID SGU60 meets the following properties:



PROPERTY	TEST METHOD	ENGLISH	METRIC
Ultimate Tensile Strength	<u>ASTM D-6637</u>	4,111 lbs/ft	60 kN/m
Creep Limited Strength		2,855 lbs/ft	41.7 kN/m
(LTDS) Long Term Design Strength (sand/silt/clay)		2,359 lbs/ft	34.4 kN/m
Partial Factor -Environmental Effects Environment, 3 < pH < 9	GRI-GG7, GRI-GG8)	1.1 RFd	1.1 RFd
Partial Factor -Installation Damage (sand/silt/clay)	ASTM D 5818	1.1 RFid	1.1 RFid
Reduction Factor - Creep (@20°C, 114 years design life)		1.44	1.44

SGU60 Shipping & Packaging Information

SIZE	DIAMETER	WIDTH	WEIGHT	AREA	ROLLS PER TRAILER
6.25' x 288'	10"	6.25'	94 lbs	200 y ²	352
12.5' x 288'	12"	12.5'	202 lbs	400 y ²	212

US Fabrics, Inc. | 3904 Virginia Avenue | Cincinnati, OH 45227
Phone: (800) 518-2290 | Fax: (513) 271-4420 | email: info@usfabrics.com

This information is provided for reference only and is not intended as a warranty or guarantee.
 US Fabrics assumes no liability in connection with the use of this information.