




# AWD SITEDRAIN 306W

## Prefabricated Drainage Composite



- Core Type:** Solid, Dimpled Polymeric
- Core Compressive Strength:** Very High
  - 30,000 psf
- Fabric Type:** Monofilament Woven
  - Single Sided
- Flow Rate:** Moderate
  - Core: 13 g/min/f<sup>2</sup>
  - Fabric: 145 g/min/f<sup>2</sup>

Product meets the following M.A.R.V. values:

PROPERTY	TEST METHOD	ENGLISH	METRIC
CBR Puncture <span>Geotextile</span>	<u>ASTM D-6241</u>	675 lbs	3,004 N
Trapezoidal Tear <span>Geotextile</span>	<u>ASTM D-4533</u>	115 x 75 lbs	512 x 334 N
Apparent Opening Size <span>Geotextile</span>	<u>ASTM D-4751</u>	40 US Sieve	0.425 mm
Permittivity <span>Geotextile</span>	<u>ASTM D-4491</u>	2.1 Sec <sup>-1</sup>	2.1 Sec <sup>-1</sup>
Water Flow Rate <span>Geotextile</span>	<u>ASTM D-4491</u>	145 g/min/f <sup>2</sup>	5,907 L/min/m <sup>2</sup>
UV Resistance @ 500 hours <span>Geotextile</span>	<u>ASTM D-4355</u>	90 %	90 %
Thickness <span>Core</span>	<u>ASTM D-1599</u>	0.25 inches	6.35 mm
Water Flow Rate <sup>(2)</sup> <span>Core</span>	<u>ASTM D-4716</u>	13 g/min/ft	161 L/min/m <sup>2</sup>
Compressive Strength <span>Core</span>	<u>ASTM D-1621</u>	30,000 p/f <sup>2</sup>	1,436 kPa

(1) Maximum average roll value (MaxARV).

(2) In-plane flow rate measured at 360 psf compressive load and a hydraulic gradient of 1.0.

## AWD SITEDRAIN 306W Shipping & Packaging Information

SIZE	DIAMETER	WIDTH	WEIGHT	AREA	ROLLS PER TRAILER
4' x 50'	16"	4'	57 lbs	200 f <sup>2</sup>	264

**US Fabrics, Inc. | 3904 Virginia Avenue | Cincinnati, OH 45227**  
**Phone: (800) 518-2290 | Fax: (513) 217-4420 | email: [info@usfabrics.com](mailto:info@usfabrics.com)**

This information is provided for reference only and is not intended as a warranty or guarantee.  
 US Fabrics assumes no liability in connection with the use of this information.