




AWD SITEDRAIN 94T

Prefabricated Drainage Composite



- Core Type:** Solid, Dimpled Polymeric
- Core Compressive Strength:** Moderate
- 9,000 psf
- Fabric Type:** Spun-bonded nonwoven
- Single Sided
 - AASHTO Class 3
- Flow Rate:** Moderate
- Core: 12 g/min/f²
 - Fabric: 60 g/min/f²

Product meets the following M.A.R.V. values:

PROPERTY	TEST METHOD	ENGLISH	METRIC
Grab Tensile Strength Geotextile	<u>ASTM D-4632</u>	130 lbs	578 N
CBR Puncture Geotextile	<u>ASTM D-6241</u>	276 lbs	1,228 N
Trapezoidal Tear Geotextile	<u>ASTM D-4533</u>	60 lbs	267 N
Apparent Opening Size ⁽¹⁾ Geotextile	<u>ASTM D-4751</u>	60 US Sieve	0.25 mm
Permittivity Geotextile	<u>ASTM D-4491</u>	0.8 Sec ⁻¹	0.8 Sec ⁻¹
Water Flow Rate Geotextile	<u>ASTM D-4491</u>	60 g/min/f ²	2,444 L/min/m ²
UV Resistance @ 500 hours Geotextile	<u>ASTM D-4355</u>	70 %	70 %
Thickness Core	<u>ASTM D-1599</u>	0.25 inches	6.35 mm
Water Flow Rate Core	<u>ASTM D-4716</u>	12 g/min/ft	149 l/min/m
Compressive Strength Core	<u>ASTM D-1621</u>	9,000 p/f ²	431 kPa

⁽¹⁾ Maximum average roll value (MaxARV).

⁽²⁾ In-plane flow rate measured at 360 psf compressive load and a hydraulic gradient of 1.0.

AWD SITEDRAIN 94T Shipping & Packaging Information

SIZE	DIAMETER	WIDTH	WEIGHT	AREA	ROLLS PER TRAILER
4' x 50'	16"	4'	29 lbs	200 f ²	468

US Fabrics, Inc. | 3904 Virginia Avenue | Cincinnati, OH 45227
Phone: (800) 518-2290 | Fax: (513) 217-4420 | email: info@usfabrics.com

This information is provided for reference only and is not intended as a warranty or guarantee.
 US Fabrics assumes no liability in connection with the use of this information.