





AWD SITEDRAIN DS303

Prefabricated Drainage Composite



Core Type: Perforated, Dimpled Polymeric

Core Compressive Strength: Very High

- 30,000 psf

Fabric Type: Needle-punched nonwoven

- Double Sided

Flow Rate: Moderate

- Core: 13 g/min/f²

- Fabric: 150 g/min/f²

Product meets the following M.A.R.V. values:

PROPERTY	TEST METHOD	ENGLISH	METRIC
Grab Tensile Strength Geotextile	<u>ASTM D-4632</u>	80 lbs	356 N
CBR Puncture Geotextile	<u>ASTM D-6241</u>	210 lbs	934 N
Trapezoidal Tear Geotextile	<u>ASTM D-4533</u>	30 lbs	133 N
Apparent Opening Size ⁽¹⁾ Geotextile	<u>ASTM D-4751</u>	50 US Sieve	0.3 mm
Permittivity Geotextile	<u>ASTM D-4491</u>	2.2 Sec ⁻¹	2.2 Sec ⁻¹
Water Flow Rate Geotextile	<u>ASTM D-4491</u>	150 g/min/f ²	6,112 L/min/m ²
UV Resistance @ 500 hours Geotextile	<u>ASTM D-4355</u>	70 %	70 %
Thickness Core	<u>ASTM D-1599</u>	0.25 inches	6.35 mm
Water Flow Rate ⁽²⁾ Core	<u>ASTM D-4716</u>	13 g/min/ft	161 L/min/m ²
Compressive Strength Core	<u>ASTM D-1621</u>	30,000 p/f ²	1,436 kPa

⁽¹⁾ Maximum average roll value (MaxARV).

⁽²⁾ In-plane flow rate measured at 360 psf compressive load and a hydraulic gradient of 1.0.

AWD SITEDRAIN DS303 Shipping & Packaging Information

SIZE	DIAMETER	WIDTH	WEIGHT	AREA	ROLLS PER TRAILER
4' x 50'	17"	4'	58 lbs	200 f ²	312

US Fabrics, Inc. | 3904 Virginia Avenue | Cincinnati, OH 45227
Phone: (800) 518-2290 | Fax: (513) 217-4420 | email: info@usfabrics.com

This information is provided for reference only and is not intended as a warranty or guarantee.
 US Fabrics assumes no liability in connection with the use of this information.