





AWD SITEDRAIN DS98

Prefabricated Drainage Composite



Core Type: Perforated, Dimpled Polymeric

Core Compressive Strength: Moderate

- 9,000 psf

Fabric Type: Needle-punched nonwoven

- Double Sided

- AASHTO Class 1

Flow Rate: Moderate

- Core: 12 g/min/f²

- Fabric: 100 g/min/f²

Product meets the following M.A.R.V. values:

PROPERTY	TEST METHOD	ENGLISH	METRIC
Grab Tensile Strength Geotextile	<u>ASTM D-4632</u>	205 lbs	912 N
CBR Puncture Geotextile	<u>ASTM D-6241</u>	535 lbs	2,381 N
Trapezoidal Tear Geotextile	<u>ASTM D-4533</u>	80 lbs	356 N
Apparent Opening Size Geotextile	<u>ASTM D-4751</u>	80 US Sieve	0.177 mm
Permittivity Geotextile	<u>ASTM D-4491</u>	1.4 Sec ⁻¹	1.4 Sec ⁻¹
Water Flow Rate Geotextile	<u>ASTM D-4491</u>	100 g/min/f ²	4,074 L/min/m ²
UV Resistance @ 500 hours Geotextile	<u>ASTM D-4355</u>	70 %	70 %
Thickness Core	<u>ASTM D-1599</u>	0.25 inches	6.35 mm
Water Flow Rate Core	<u>ASTM D-4716</u>	12 g/min/ft	149 l/min/m
Compressive Strength Core	<u>ASTM D-1621</u>	9,000 p/f ²	431 kPa

(1) Maximum average roll value (MaxARV).

(2) In-plane flow rate measured at 360 psf compressive load and a hydraulic gradient of 1.0.

AWD SITEDRAIN DS98 Shipping & Packaging Information

SIZE	DIAMETER	WIDTH	WEIGHT	AREA	ROLLS PER TRAILER
4' x 50'	17"	4'	38 lbs	200 f ²	432

US Fabrics, Inc. | 3904 Virginia Avenue | Cincinnati, OH 45227
Phone: (800) 518-2290 | Fax: (513) 217-4420 | email: info@usfabrics.com

This information is provided for reference only and is not intended as a warranty or guarantee.
 US Fabrics assumes no liability in connection with the use of this information.