



Synteen SC52K is composed of high molecular weight, high tenacity multifilament polyester yarns that are woven into a stable network placed under tension. Synteen SC52K is inert to biological degradation and is resistant to naturally encountered chemicals, alkalis and acids.



PROPERTY	TEST METHOD	ENGLISH	METRIC
Ultimate Tensile Strength	ASTM D-4595	55,000 lbs/ft	802.7 kN/m
Tensile Strength @ 5 % Strain	ASTM D-4595	20,000 lbs/ft	291.9 kN/m
(LTDS) Long Term Design Strength	GRI-GT7	28,062 lbs/ft	409.5 kN/m
Partial Factor -Environmental Effects Environment, 3 < pH < 9	GRI-GG7, GRI-GG8)	1.1 RFd	1.1 RFd
Partial Factor -Installation Damage (sand/silt/clay)	ASTM D 5818	1.18 RFid	1.18 RFid
Reduction Factor - Creep		1.51	1.51

Synteen SC52K Shipping & Packaging Information

SIZE	WIDTH	AREA
16.4' x 300'	16.4'	546.67 y²