





US 220GN Geonet



A 200 mil HDPE Geonet. Transnet three-dimensional, bi-planer geonets are manufactured from high-density polyethylene (HDPE) resin formulated with 2.0 % carbon black.



PROPERTY	TEST METHOD	ENGLISH	METRIC
Thickness ⁽³⁾	ASTM D-5199	200 mils	5.08 mm
Tensile Strength ⁽³⁾	ASTM D-7179	45 lbs/in	7.87 N/mm
Transmissivity ^(1,3)	ASTM D-4716	9.67 g/min/f ²	2.0 x 10 ⁻³ m ² /sec
Carbon Black ⁽³⁾	ASTM D-4218	2 %	2 %
Density ⁽³⁾	ASTM D-1505	0.94 g/cm ³	0.94 g/cm ³
Melt Flow ⁽²⁾	ASTM D-1238	1 g/10 min (max)	1 g/10 min (max)

⁽¹⁾ Transmissivity measured using water at 21 ± 2 ° C (70 ± 4) ° C with a gradient of 0.1 and a confining pressure of 10,000 psf between steel plates after 15 minutes. Values may vary with individual labs.

⁽²⁾ Condition 190/2.16.

⁽³⁾ Minimum average value.

US 220GN Shipping & Packaging Information

SIZE	DIAMETER	WIDTH	WEIGHT	AREA	ROLLS PER TRAILER
14.5' x 300'	33"	14.5'	950 lbs	4,350 f ²	27

US Fabrics, Inc. | 3904 Virginia Avenue | Cincinnati, OH 45227
Phone: (800) 518-2290 | Fax: (513) 271-4420 | email: info@usfabrics.com

This information is provided for reference only and is not intended as a warranty or guarantee.
US Fabrics assumes no liability in connection with the use of this information.