US 330NWE-A

AREMA Medium Survivability Nonwoven Geotextile

US 330NWE-A is a 12 OZ MARV WEIGHT nonwoven needlepunched geotextile made of 100% polypropylene staple filaments. US 330NWE-A is resistant to ultraviolet deterioration, rotting, biological degradation, naturally encountered chemicals, alkalis and acids. Polypropylene is stable within a pH range of 2 to 13. US 330NWE-A meets AREMA specification 1-10-2, "Heavy Survivability" and the following M.A.R.V. values:

PROPERTY	TEST METHOD	ENGLISH	METRIC
Weight	ASTM D-5261	12 oz/y²	406.8 g/m²
Grab Tensile Strength	ASTM D-4632	225 lbs	1,001 N
Elongation @ Break	ASTM D-4632	20 %	20 %
Mullen Burst	ASTM D-3786	450 psi	3,102 kPa
Pin Puncture	ASTM D-4833	150 lbs	667 N
Trapezoidal Tear	ASTM D-4533	125 lbs	556 N
Apparent Opening Size(1,2)	ASTM D-4751	70 US Sieve	0.21 mm
Permittivity(1)	ASTM D-4491	0.25 Sec^{-1}	0.25 Sec^{-1}
Permeability(1)	ASTM D-4491	0.1 cm/sec	0.1 cm/sec
UV Resistance @ 500 Hours	ASTM D-4355	70 %	70 %
Transmissivity(3,4)	ASTM D-4716		6.2 x 10^{-6} m²/sec
Abrasion Resistance	ASTM D-4886	80 %	80 %

(1) At the time of manufacturing. Handling, storage, and shipping may change these properties.
(2) Maximum average roll value (MaxARV).
(3) Transmissivity measured using water at 21 ± 2 ° C (70 ± 4) ° C with a gradient of 0.1 and a confining pressure of 10,000 psf between steel plates after 15 minutes. Values may vary with individual labs.
(4) Minimum average value.

US 330NWE-A Shipping & Packaging Information

SIZE	DIAMETER	WIDTH	WEIGHT	AREA	ROLLS PER TRAILER
15' x 300'	27"	15'	395 lbs	500 y²	80

US Fabrics, Inc. | 3904 Virginia Avenue | Cincinnati, OH 45227
Phone: (800) 518-2290 | Fax: (513) 271-4420 | email: info@usfabrics.com

This information is provided for reference only and is not intended as a warranty or guarantee.
US Fabrics assumes no liability in connection with the use of this information.