



US 425NWE-A

AREMA Extra Heavy Survivability Nonwoven Geotextile



US 425NWE-A is a 16 OZ MARV WEIGHT nonwoven needlepunched geotextile made of 100% polypropylene staple filaments. US 425NWE-A is resistant to ultraviolet deterioration, rotting, biological degradation, naturally encountered bases and acids. Polypropylene is stable within a pH range of 2 to 13. US 425NWE-A meets AREMA specification 1-10-2, "Extra Heavy Survivability" and the following M.A.R.V. values:



PROPERTY	TEST METHOD	ENGLISH	METRIC
Weight	<u>ASTM D-5261</u>	16 oz/y ²	542.4 g/m ²
Grab Tensile Strength	<u>ASTM D-4632</u>	350 lbs	1,558 N
Elongation @ Break	<u>ASTM D-4632</u>	20 %	20 %
Mullen Burst	<u>ASTM D-3786</u>	450 psi	3,102 kPa
Pin Puncture	<u>ASTM D-4833</u>	185 lbs	823 N
Trapezoidal Tear	<u>ASTM D-4533</u>	150 lbs	668 N
Apparent Opening Size ^(1,2)	<u>ASTM D-4751</u>	70 US Sieve	0.21 mm
Permittivity ⁽¹⁾	<u>ASTM D-4491</u>	0.2 Sec ⁻¹	0.2 Sec ⁻¹
Permeability ⁽¹⁾	<u>ASTM D-4491</u>	0.1 cm/sec	0.1 cm/sec
UV Resistance @ 500 Hours	<u>ASTM D-4355</u>	70 %	70 %
Transmissivity ^(3,4)	<u>ASTM D-4716</u>		9.3 x 10 ⁻⁶ m ² /sec
Abrasion Resistance	<u>ASTM D-4886</u>	80 %	80 %

(1) At the time of manufacturing. Handling, storage, and shipping may change these properties.

(2) Maximum average roll value (MaxARV).

(3) Transmissivity measured using water at 21 ± 2 ° C (70 ± 4) ° C with a gradient of 0.1 and a confining pressure of 10,000 psf between steel plates after 15 minutes. Values may vary with individual labs.

(4) Minimum average value.

US 425NWE-A Shipping & Packaging Information

SIZE	DIAMETER	WIDTH	WEIGHT	AREA	ROLLS PER TRAILER
15' x 360'	31"	15'	620 lbs	600 y ²	27

US Fabrics, Inc. | 3904 Virginia Avenue | Cincinnati, OH 45227
Phone: (800) 518-2290 | Fax: (513) 271-4420 | email: info@usfabrics.com

This information is provided for reference only and is not intended as a warranty or guarantee.
US Fabrics assumes no liability in connection with the use of this information.