




# US 220/1/8GN Geocomposite



A 200 mil HDPE Geonet with a MARV 8oz nonwoven attached to one side.



PROPERTY	TEST METHOD	ENGLISH	METRIC
Thickness <sup>(5)</sup> <span>Geonet</span>	<u>ASTM D-5199</u>	200 mils	5.08 mm
Tensile Strength <sup>(5)</sup> <span>Geonet</span>	<u>ASTM D-7179</u>	45 lbs/in	7.87 N/mm
Transmissivity <sup>(1,3)</sup> <span>Geonet</span>	<u>ASTM D-4716</u>	9.67 g/min/ft	2.0 x 10 <sup>-3</sup> m <sup>2</sup> /sec
Carbon Black <sup>(5)</sup> <span>Geonet</span>	<u>ASTM D-4218</u>	2 %	2 %
Density <sup>(5)</sup> <span>Geonet</span>	<u>ASTM D-1505</u>	0.94 g/cm <sup>3</sup>	0.94 g/cm <sup>3</sup>
Melt Flow <sup>(2)</sup> <span>Geonet</span>	<u>ASTM D-1238</u>	1 g/10 min (max)	1 g/10 min (max)
Transmissivity <sup>(1,3)</sup> <span>Geocomposite</span>	<u>ASTM D-4716</u>	4.83 g/min/ft	1.0 x 10 <sup>-3</sup> m <sup>2</sup> /sec
Ply Adhesion <sup>(5)</sup> <span>Geocomposite</span>	<u>ASTM D-7005</u>	1 lbs/in	178 g/cm
Weight <sup>(7)</sup> <span>Geotextile</span>	<u>ASTM D-5261</u>	8 oz/y <sup>2</sup>	271.2 g/m <sup>2</sup>
Grab Tensile Strength <span>Geotextile</span>	<u>ASTM D-4632</u>	225 lbs	1,001 N
Elongation @ Break <span>Geotextile</span>	<u>ASTM D-4632</u>	50 %	50 %
CBR Puncture <span>Geotextile</span>	<u>ASTM D-6241</u>	600 lbs	2,670 N
Trapezoidal Tear <span>Geotextile</span>	<u>ASTM D-4533</u>	90 lbs	401 N
Apparent Opening Size <span>Geotextile</span>	<u>ASTM D-4751</u>	80 US Sieve	0.177 mm
Permittivity <sup>(1)</sup> <span>Geotextile</span>	<u>ASTM D-4491</u>	1.26 Sec <sup>-1</sup>	1.26 Sec <sup>-1</sup>
Permeability <sup>(1)</sup> <span>Geotextile</span>	<u>ASTM D-4491</u>	0.3 cm/sec	0.3 cm/sec
Water Flow Rate <span>Geotextile</span>	<u>ASTM D-4491</u>	100 g/min/f <sup>2</sup>	4,074 L/min/m <sup>2</sup>

<sup>(1)</sup> At the time of manufacturing. Handling, storage, and shipping may change these properties. <sup>(2)</sup> Maximum average roll value (MaxARV). <sup>(3)</sup> Transmissivity measured using water at 21 ± 2 ° C (70 ± 4) ° C with a gradient of 0.1 and a confining pressure of 10,000 psf between steel plates after 15 minutes. Values may vary with individual labs. <sup>(4)</sup> Condition 190/2.16. <sup>(5)</sup> Minimum average value. <sup>(6)</sup> Maximum. <sup>(7)</sup> Minimum average roll value (M.A.R.V.).

## US 220/1/8GN Shipping & Packaging Information

SIZE	DIAMETER	WIDTH	WEIGHT	AREA	ROLLS PER TRAILER
14.5' x 275'	33"	14.5'	1,200 lbs	3,987.5 f <sup>2</sup>	27

**US Fabrics, Inc. | 3904 Virginia Avenue | Cincinnati, OH 45227**  
**Phone: (800) 518-2290 | Fax: (513) 217-4420 | email: [info@usfabrics.com](mailto:info@usfabrics.com)**

This information is provided for reference only and is not intended as a warranty or guarantee.  
 US Fabrics assumes no liability in connection with the use of this information.